

DIVERSIFIED
TESTING LABORATORIES, INC.

"We Test Per Your Request"

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
 www.diversifiedtestinglabs.com

June 12, 2009

Mr. Clyde Hall
 AURORA SPECIALTY TEXTILES GROUP, INC.
 P.O. Box 1107
 Travelers Rest, SC 29690

Reference: Laboratory Test Report
 Lab Identification No. 1087
 Invoice No. 22469 (Attached)

Dear Mr. Hall:

One (1) fabric sample, identified as **MTJ40202 REPLAY II**, was received and tested in accordance with the National Fire Prevention Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2004 Edition, (Test 1, Small Scale)". The results are as follows:


<u>Specimen Number</u>	<u>Residual Flame (seconds)</u>	<u>Weight Loss (percent)</u>
1	0.0	21.44
2	0.0	28.45
3	0.0	23.48
4	0.0	23.06
5	0.0	18.86
6	0.0	22.62
7	0.0	19.44
8	0.0	20.52
9	0.0	20.57
10	0.0	19.07
AVG.	0.0*	21.75

*0.0 seconds indicate no flaming combustion or molten material (drops) that drop to the test chamber floor.

The fabric sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,


 Karon S. Matkins

KSM/mr

Attachment

OUR LETTERS AND REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.